



2450 MASKING TAPE

**WHITE/YELLOW SATURATED PAPER
SOLVENT BASED ADHESIVE**

TEST		NOMINAL	UNITS	ACCEPTABLE Minimum/maximum	TEST METHOD
1 Thickness:	Total	105	μ	90 ÷ 130	PSTC 33
	Backing	90		70 ÷ 110	
2 Weight:	Total	89		81 ÷ 97	ISO 536
	Backing	59	g/m ²	53 ÷ 65	
	Adhesive	30		28 ÷ 32	
3 Adhesion to:	Steel	4,25	N/25 mm.	2,5 ÷ 6	PSTC 1
	Backing	2		1,25 ÷ 3,75	
4 Shear Adhesion	(50° 1 kg) Met	> 15	min.	> 15	
5 Tensile strength MD		87,5	N/25 mm.	70 ÷ 112,5	PSTC 31
6 Elongation to break %		8,5	%	5 ÷ 12	PSTC 31
7 RBT		1	cm	0 ÷ 3	PSTC 6

TESTING CONDITIONS: TEMPERATURE 23 °C ± 2 / RELATIVE HUMIDITY 50% ± 5

Note: We advise to test the material in relation to required application. The company reserves the right to improve products and change specifications, which may alter performance.